

20030 senago (milano) via piemonte,18 tel.02.99014.1 centralino www.alcea.com

 Date: 04/08/2021
 TECHNICAL DATA SHEET
 Page 1/2

PRODUCT NAME & CODE: GEOCRIL 445x/H

DESCRIPTION: ACRYLIC WATERBASE CLEAR 2K

COLOUR: TRANSPARENT

NATURE AND FIELD OF USE

GEOACRIL is a two-component polyacrylic converter to be pigmented with GEOCOLOR series pastes, designed for painting furnishing elements, such as cabinets, doors, tables, shelves and in general wooden products for interiors that require excellent chemical-physical resistance.

PREPARATION OF PRODUCT

CATALYST RATIOBY VOLUME
BY WEIGHT
CATALYST
100% of Part A
10%
10%
4350/A699

DILUTION:

10 to 20% (on Part 'A') for spray applications (gravity cup gun and air-mix).

POT-LIFE:

With 4350/A699 and dilution of 20%, pof life >2 hours at a temperature of 20°C/68°F and RH of 60-70%.

AVAILABLE GLOSSES (± 2) :

4452/H - 20 gloss 4453/H - 30 gloss

TECHNICAL CHARACTERISTICS:

PHYSICAL CHARACTERISTICS:

	Part A only	Catalyzed	Tolerance	U.O.M.	Method
Specific Weight (20°C/68°F)	1.027	1,032	$\pm 0,025$	Kg/l	ME14
Specific Weight (20°C/68°F)	8,576	8,618	$\pm 0,100$	lb/USgal	ME14
Viscosity DIN8 (20°C/68°F)	40		± 5	Sec	ME16
Weight solids	35	38.4	± 1	kg/kg	ME15
Volume / weight solids	32	34,8	± 1	l/kg	ME15
Volume solids	32.8	35,9	± 1	1/1	ME15
VOC	5		± 1	%	
VOC	51		± 10	g/l	
VOC	.41		± 0,1	lb/USgal	
Flash Point	<60 C/140 F				ME12

THEORETICAL YIELD (Dry film thickness, A+B)

THEORETICAL TILLED (DITY IN THE CHICAGO, 11 T.D)						
30 micron	10,8	m²/kg	ME82			
1 mil	615	Sqft/Usgal	ME82			



20030 senago (milano) via piemonte,18 tel.02.99014.1 centralino www.alcea.com

Date: 04/08/2021 TECHNICAL DATA SHEET Page 2/2

DRY TIMES:

Dust free	20 - 30	Minutes	ME81
Dry to touch	50 – 60	Minutes	ME81
Thoroughly dry	12- 16	Hours	ME81
Time between coats (without sanding)	60 - 120	Minutes	ME81
Time between coats (with sanding)	▶ 12	Hours	ME81

DRY FILM (Characteristics)

Excellent hardness and surface resistance.

SUBSTRATE TYPES AND PREPARATION

GEOACRIL 2K 445x / H being a finished product, it must be applied on substrates previously treated with suitable well sanded and dusted primers, such as GEOACRIL 4453/2140, GEOFOND 4781 / MSBB or GEOFOND 4671 / MSBB. Proceed with a finishing coat, applying a quantity between 80 and 100 gr / m2 and wait for the drying times.

APPLICATION PROCEDURE:

Spray: Gravity cup gun, airless or airmix. Ambient humidity between 40 and 70%.

SUBSEQUENT TREATMENT

Once dried, the product does not require further subsequent treatments.

ADDITIONAL INFORMATION

THE CATALYST MUST BE ADDED SLOWLY AND UNDER GOOD AGITATION. WE RECOMMEND MECHANICAL AGITATION FOR A FEW MINUTES.

The quantity of GEOCOLOR pastes to add to the converter depends on the type of color you want to make. On average, a pigmentation of 20% represents a good compromise between hiding power and the final aesthetic result of the paint product.

Always shake the products well before use.

After use, it is advisable to always close the package carefully.

In case of decanting, use only containers made of suitable material, such as polyethylene and stainless steel. For best aesthetic results, prepare the substrate paying attention to sanding.

At the end of processing, wash the tools used thoroughly with water.

The final result of the painting cycle is the sole responsibility of the user, who must ensure that the product corresponds to their needs.

Our company, unable to ensure control of the painting process carried out by the user, cannot therefore take on any responsibility for the final result achieved through the use of its products.

Our company, on the other hand, guarantees the constancy of the chemical-physical characteristics of the product indicated in this Technical Data Sheet.

STORAGE AND SHELF LIFE

Attention, the product must be stored in its original containers, away from heat sources, at temperatures between +5 °C (+41 °F) and +35 °C (+95 °F). The product kept in the aforementioned conditions has a stability of 24 months from the date of production.

The indications of this newsletter are the result of numerous experiments and should be considered as excellent orientation indicators. However, the methods of application and processing systems are very varied, therefore no guarantee can be assumed for each individual case. This updated version cancels and replaces previous editions.