

PU Dispersion

150.90/91

Application: Laminating adhesive for the manufacture of three-dimensional coated furniture parts with thermoplastic foils (e.g. PVC).
The properties of the bonded parts and, where necessary, the surfaces of the materials have to undergo application-related testing prior to use.

Typical Key Data/ Directions for Use: PU dispersion with built-in crosslinking mechanism. The adhesive can be processed in one-component form, i.e. without the addition of a crosslinking agent.

Laminating is to be carried out within the first 8 hours after adhesive application. The processing characteristics may vary depending on the application technology, which can affect the bonding process.

Customer trials are required.

Adhesive application:

In general, the adhesive is applied to one surface by spraying onto the carrier part.

Application amount:

80 – 130 g/m² wet application to the MDF edge (the application of two layers with short drying in between is recommended) and 50 – 70 g/m² wet application to the MDF surface; see also "Requirements for a High-Quality Bonding Process" (below).

The temperature inside the glue line is decisive for the bonding result.

Minimum reactivation temperature

inside the glue line [°C]: ≥ 55
(depending on the pressure and time in the press)

We recommend that all materials coming into contact with the glue are made of high-quality stainless steel (German standard V2A according to DIN EN 10027 – W-No. 1.4301 or better quality) or of inert plastics, e.g. Teflon, PP, polyamide. Avoid contact with other metals like zinc, brass, copper or aluminum. For more information, please contact the equipment manufacturer or our technical service.

Minimum processing temperature for

materials, adhesive and ambient air [°C]: 15 (not identical with MFFT)

Appearance: final digit 0 = white opaque
final digit 1 = white

Key data measured according Jowat test methods.

Requirements for a High-Quality Bonding Process:

The properties (e.g. surface tension, plasticizer content...) and the conditioning of the substrates, as well as the processing conditions (e.g. ambient temperature, humidity...) will influence the processes of joining and bonding. Customer tests under consideration of everyday production conditions are therefore absolutely necessary to define stable process parameters and to ensure that the product is fit for purpose. For best bonding results, the materials to be bonded should be free of dust, oil, and grease, and be dry. Wood moisture content should be at 6 ± 2 %. Ideally, the minimum temperature should be at 18 °C. Avoid draft.

continued on page 2

03/22 All data indicated are characteristics represented as average values. Our technical data sheets are periodically revised to represent the latest state of technology. This edition is replacing and superseding all previous ones, and is valid on the date of compilation.
Please refer to the last page of this technical data sheet for additional information.

Jowat 
Klebstoffe

Our Application Technology Department and our Application Specialists will provide technical data to assist you in your choice of an appropriate product for your requirements. Please observe the information in the section “Remarks.” As a suggestion on how to establish high-quality bonding processes, please refer to DIN 2304 and the “3D Furniture Front Production Quality Guide” (published by: Industrieverband Kunststoffbahnen e.V. and Industrieverband Klebstoffe e.V.).

Specification:	Viscosity at 20 °C [mPas]:	3,000 ± 500
	(Brookfield, RV, spindle 3, 20 rpm)	
	Density at 20 °C [g/cm³]:	1.05 ± 0.02
	(pycnometer, 100 ml)	
	Solids content, 7 min at 115 °C [%]:	40.0 ± 2.0
	(Jowat test method)	
	pH value at 20 °C:	8.0 ± 1.0
	(Jowat test method)	

The values are always determined on the date of production.

Cleaning: Machines and equipment may be cleaned after use with cold or warm water, using Jowat® Cleaner Concentrate 192.40.

Safety Considerations: In case of spray application: do not inhale the atomized material. Observe the safety data sheet. Especially open applicator systems require an extraction.

Storage: The product should remain stored in properly closed original containers, dry and cool (15 – 20 °C). Lower temperatures between 6 °C and 14 °C are permissible during transport, for a max. duration of 14 days. Verify and document the temperature when the goods are received. Before processing, the adhesive has to be conditioned by storing at 15 – 25 °C. For best-before date, please see container label. After the elapse of the best-before date, it is essential that you again verify that the product is fit for your intended application.

Packaging: Information about packaging types and units is available upon request.

Remarks: **For further information concerning safety, handling, transport and disposal, please refer to the safety data sheet.** The information on this data sheet is based on test results from our laboratories as well as on reported experience gained in the field by our customers. It can, however, not cover all parameters for each specific application and is therefore not binding upon Jowat, nor should it be relied upon in lieu of your own required testing. The information given in this leaflet does not represent a performance guarantee. Unless otherwise agreed with our customers, the values stated in the section “Specification” shall be regarded as the finally agreed upon product properties. No liability may be derived from the information contained herein nor from the information provided by our free technical advisory service.

Jowat Information

Gluing as one of the most efficient methods of bonding is constantly gaining importance and expanding into new areas of application. At the same time, the number of substrates to be bonded is also growing at an unprecedented rate. New methods and equipment to process adhesives are developed.

The in-house R & D departments of Jowat are responding with intensive efforts to keep pace with these constant changes. A highly qualified team of chemists and engineers is using the latest techniques and brightest ideas to provide the utmost in advice our customers and to make sure that they get the adhesive which meets their needs.

Our information is based on test results from our laboratories as well as on experience gained in the field by our customers. This advice, however, cannot cover all eventualities for each specific application and as such is not binding for us. Please, contact our technical service department in each case to find out what the actual technical state of development for the respective product is, and request the latest data sheet. Any use of our product without this precautionary measure would be your sole responsibility.

The processing company itself must therefore test the adhesives manufactured by us for suitability in each individual case. This applies to the first use of a sample as well as to modifications during an ongoing production.

We are therefore requesting all our new customers to test our adhesives for suitability on original parts at conditions equal to normal processing conditions. The bond has then to be subjected to the actual stress which it would undergo when in use and has to be assessed. This test is absolutely necessary.

Customers who undertake modifications during a running production are requested to pass this information on to us. Please notify us when machines are set to new parameters as well as when the substrates to be bonded are changed. Only then will Jowat be able to provide our most up-to-date information to the processor using our adhesives.

The information given in this leaflet is based on practical experience and on results of tests in our laboratory, and does in no way constitute any guarantee of properties. No liability may be derived from these indications nor from the recommendations made by our technical advisory service.