

Copolymer

Application: Especially designed for priming HPL edgebanding to be bonded with Jowatherm EVA

based edgebanding hot melt.

Characteristics/ **Directions for** 

Low to medium viscosity copolymer emulsion with excellent adhesion to coated surfaces.

use:

Mix 1:1 with water. Brush on an even coating and let dry thoroughly prior to

edgebanding.

During storage, the viscosity of the product may increase. High storage temperatures promote higher increase in viscosity. We recommend the use of a suitable tool to stir the

product before use.

15 (58°F) (not identical with minimum film-Min. temperature for materials, glue

and room air [°C]: forming temperature) Application amount: 1.5-2.0 mil wet-3-5 g/sqft

Appearance of the glue film: Transparent

Density at 20 °C (68 °F) [g/cm<sup>3</sup>]: approx.  $1.05 \pm 0.05$  (8.7 lbs/gal)

Our Application Technology Department and our application specialist will provide technical data to assist you in your choice of an appropriate adhesive for your requirements. Please observe the information on the section "remarks".

Specification: Viscosity at 25 °C (77 °F) [mPas]: approx.  $2,000 \pm 1,000$ 

(Brookfield, RV, spindle 5, 20 RPM)

approx.  $70 \pm 2$ Solids cont., 2h at 90 °C (194 °F) [%]:

(Jowat test method)

 $4.5 \pm 1$ pH value:

(Jowat test method)

General bonding requirements: The properties (e.g. surface tension, plasticiser content....) and the conditioning of the

substrates, as well as the processing conditions (e.g. ambient temperatures,

humidity...) will influence the processes of joining and bonding. Customer tests under consideration of everyday production conditions are therefore absolutely necessary to define stable process parameters and to ensure that the product is fit for purpose. For best bonding results, the materials to be bonded should be free of dust, oil and grease, and be dry. Ideally, the minimum temperature should be at 18 °C (64 °F). Avoid

draught.

Cleaning: Machines and equipment may be cleaned after use with warm or cold water. Dried glue

must be removed mechanically.

Storage: The product should remain stored in properly closed original containers, cool and dry.

For best before date, please refer to label on the packaging unit.

Packaging: Information about packaging types and units is available upon request.

Remarks: For further information concerning handling, transport and disposal, please refer

to the Safety Data Sheet.

The information on this data sheet is based on test results from our laboratories as well as on reported experience gained in the field by our customers. It can, however, not cover all parameters for each specific application and is therefore not binding upon Jowat, nor

Page 1 of 3

03/20 All data indicated are characteristics represented as average values. Our technical data sheets are constantly revised to represent the latest state of technology. This edition is replacing all previous ones, and is valid on the date of compilation.





Copolymer 148.50

should it be relied upon in lieu of your own required testing. The information given in this leaflet represents neither a performance guarantee nor a guarantee of properties, nature, condition, state or quality. No liability may be derived from the information contained herein nor from the information provided by our free technical advisory service.

## **JOWAT Corporation Information**

Gluing, as one of the most efficient methods of bonding, is constantly expanding into new areas of application. At the same time, the number of substrates to be bonded is also growing at an unprecedented rate. New methods and equipment to process adhesives are constantly being improved and developed.

The in-house R&D department of JOWAT Corporation ("JOWAT") is responding with intensive efforts to keep pace with these constant changes. A highly trained and qualified team of chemists and engineers are using the latest techniques and the brightest ideas to make sure that our adhesives meet the needs of our customers for new and innovative applications.

We have assimilated information based on test results from our laboratories as well as on experience gained in the field by working with our customers. This information is available by contacting our technical service department. Customers who have obtained information and thereafter undertake modifications during a running production are invited to provide this information to us to assist us in maintaining our field information and obtain any updated information we may have. However, any technical information we provide is provided for informational and assistance purposes only, and should not be relied upon or used to replace field testing by the user of the adhesive in the actual application for which the adhesive is to be used. Our laboratory testing and field information obtained cannot simulate all eventualities that may occur in each specific application, and for that reason we cannot and do not insure performance or results in specific applications.

Any user of adhesives manufactured by JOWAT must test the adhesive(s) for suitability in each individual application, performing such tests in connection with the first use of a sample as well as all subsequent modifications during any ongoing production.

In addition to such other tests the users of our adhesives deem appropriate to insure suitable bonding, all users of adhesives manufactured by JOWAT should test the adhesives for suitability on original parts equal to normal processing conditions. The adhesive bond should then also be tested and assessed by subjecting it to the actual stress and conditions it will undergo in its intended use. ALL OF THESE TESTS ARE ABSOLUTELY NECESSARY AND MUST BE PERFORMED.

IMPORTANT: Any products (the "Products") manufactured by JOWAT, its parent, affiliates and subsidiaries ("Seller"), as well as all services relating to such Products are subject to the JOWAT Corporation General Terms and Conditions. THE WARRANTY CONTAINED HEREIN IS EXCLUSIVE AND EXPRESSLY IN LIEU OF ALL OTHER WARRANTIES, WRITTEN, ORAL, IMPLIED OR STATUTORY, INCLUDING BUT NOT LIMITED TO EXPRESSED OR IMPLIED WARRANTIES OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE. IN ADDITION, SELLER SHALL NOT BE LIABLE FOR ANY LOSS, DAMAGE OR INJURY OF ANY NATURE, EITHER DIRECT, INDIRECT OR CONSEQUENTIAL, IN CONNECTION WITH OR RESULTING FROM THE PURCHASE, USE OR SALE OF THE PRODUCTS. SELLER'S OBLIGATION UNDER THIS WARRANTY SHALL BE LIMITED TO CREDITING BUYER WITH THE INVOICE VALUE OF ANY NONCONFORMING PRODUCTS UPON THEIR RETURN TO SELLER OR





Copolymer 148.50

REPAIRING OR REPLACING ANY NONCONFORMING PRODUCTS, IN SELLER'S SOLE DISCRETION. If an additional copy of the General Terms and Conditions is needed, please contact JOWAT.